




MICHAEL BALLANCE
PLASTICS LIMITED
SPECIALISTS IN PLASTICS AND CHEMICALS



TECHNICAL DATA SHEET

GRADE: RAVLEK I46 CPE

Chlorinated Polyethylene (CPE) Impact Modifier

APPLICATION

Window profiles, door frames, sidings/cladding, pipes and sheet.

FEATURES

CPE Impact Modifiers show excellent impact properties with flame retardancy.

BASIC PROPERTIES

Chlorine content (%)	35
Volatiles (%)	<0.5
Residue on sieve, 0.9mm sieve (%)	<2.0
Shore hardness (A)	<65
Apparent density (g/ml)	>0.50
Tensile strength (Mpa)	>8
Remaining Crystallinity	<2

Packaging: We offer 25kg bags and bulk bags

The above results are typical values and do not constitute a specification.

Please call or email for further information on any of our products

T +44(0)1283 511632 **E** sales@ballance-plastics.co.uk

or visit our **website** www.ballance-plastics.co.uk